

USABC Goals for Advanced Batteries for EVs

Parameter(Units) of fully burdened system	Minimum Goals for Long Term Commercialization	Long Term Goal
Power Density(W/L)	460	600
Specific Power – Discharge, 80% DOD/30 sec(W/kg)	300	400
Specific Power - Regen, 20% DOD/10 secW/kg	150	200
Energy Density - C/3 Discharge Rate(Wh/L)	230	300
Specific Energy - C/3 Discharge Rate(Wh/kg)	150	200
Specific Power/Specific Energy Ratio	2:1	2:1
Total Pack Size(kWh)	40	40
Life(Years)	10	10
Cycle Life - 80% DOD (Cycles)	1,000	1,000
Power & Capacity Degradation(% of rated spec)	20	20
Selling Price - 25,000 units @ 40 kWh(\$/kWh)	<150	100
Operating Environment(°C)	-40 to +50 20% Performance Loss (10% Desired)	-40 to +85
Normal Recharge Time	6 hours (4 hours Desired)	3 to 6 hours
High Rate Charge	20-70% SOC in <30 minutes @ 150W/kg (<20min @ 270W/kg Desired)	40-80% SOC in 15 minutes
Continuous discharge in 1 hour - No Failure(% of rated energy capacity)	75	75